

FORMULATION

Formulation No. 260203A-5-C1

PHASE	INCI NAME	COMMERCIAL NAME	Q'TY
A	Mica	Sericite SL	31.50
A	Synthetic Wax	AriaVel™	5.00
B	Synthetic Fluorophlogopite (and) Hydrogen Dimethicone	NK-10G-SI	18.00
B	Silica	Spheron P-1500 Silica	2.00
B	Lauroyl Lysine	AmiLube™ LL MB	3.00
B	Titanium Dioxide (CI 77891)	4P0748	10.00
B	Iron Oxides (CI 77491)	4P3511	3.00
B	Dimethicone (and) Dimethiconol	BELSIL® GB 1020	2.00
B	Dimethicone	BELSIL® DM 10	3.00
C	Pentaerythrityl Tetraisostearate	Corum 5041	2.00
C	Caprylyl Glycol (and) Phenoxyethanol (and) Hexylene Glycol	Jeecide® CAP-2	0.50
D	Synthetic Fluorophlogopite (and) Titanium Dioxide (and) Tin Oxide	Twinklepearl 411	20.00
			100.00

INSTRUCTIONS

1. Put Part A in chalking machine, and mix until uniform.
2. Add Part B to Part A, and mix well.
3. Remove some of the powder from chalking machine and mix well with Part C. Then add back into chalking machine, and mix until uniform.
4. Add Part D and stir manually until well combined.
5. Take out of the powder, and press at 200psi three times.

APPEARANCE

Coral Orange Pearl-finish Powder

For reference only / not for commercial use